

BEST AVAILABLE COPY
Europäisches
Patentamt

European
Patent Office

PCT/EP 03/01896
10/506698 PCT.

Office européen
des brevets

REC'D 31 MAR 2003

WIPO PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02405171.6

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.



R C van Dijk

DEN HAAG, DEN
THE HAGUE,
LA HAYE, LE

31/10/02



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

**Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation**

Anmeldung Nr.:
Application no.:
Demande n°: 02405171.6

Anmeldetag:
Date of filing: 06/03/02
Date de dépôt:

Anmelder:
Applicant(s):
Demandeur(s):
Ciba Specialty Chemicals Holding Inc.
4057 Basel
SWITZERLAND

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:

Enzymatic process for preparing organosilicon group containing photoinitiators

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:

C12P9/00, C07F7/08

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing:
Etats contractants désignés lors du dépôt:

AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE/TR

Bemerkungen:
Remarks:
Remarques:

See for original title of the application page 1 of the description

- 1 -

Novel process for preparing organosilicon group containing photoinitiators

The present invention relates to a novel process for preparing organosilicon group containing photoinitiators by esterifying or transesterifying of carboxylic acids or carboxylates containing a photolabile functional group with a carbinol terminated organosilicon compound in the presence of an enzyme, which catalyzes the esterification or transesterification reaction.

US Patent 6,288,129 describes a process for esterifying or transesterifying acrylic acid and/or methacrylic acid or acrylic esters and/or methacrylic esters with hydroxy-functional and/or polyoxyalkylene-modified siloxane derivatives.

Organosilicon group containing photoinitiators may be obtained in a variety of ways. For example, they may be prepared by reacting a photoinitiator with at least one alkenyl radical and a siloxane in the presence of a platinum or rhodium catalysts as described, for example in US 4,507,187.

The European Patent Publication EP-A 1072 326 describes, for example, the reaction of 2-hydroxy-2-methyl-1-[4-(2-propenyloxy)phenyl]-1-propanone with 1,1,1,3,5,5,5-heptamethyltrisiloxane in the presence of a platinum catalyst.

The International Application PCT/EP/01/09123 describes, for example, the reaction of 2-allyloxyethyl glyoxalate with 1,1,1,3,5,5,5-heptamethyltrisiloxane in the presence of a platinum catalyst.


The siloxane molecule is thermally instable and, on being exposed to an elevated temperature, siloxane fragments may be obtained. Thus, the above mentioned synthesis process generally results in undesirable byproducts which are impurities, requiring a further purification such as, for example, purification by chromatography.

The problem to be solved is to provide a process for preparing organosilicon group containing photoinitiators having no impurities or less than those prepared by conventional processes.

It has now been found that the problem can be solved using an enzymatic synthesis process.

- 2 -

Thus, the present invention relates to a process for preparing organosilicon group containing photoinitiators of the formula I



m is a number from 1 to 200; **q** is 0 or 1;


A is $\text{IN}-\text{C}(\text{O})-\text{O}-\text{CHR}_3-\text{Y}-$; **A'** is **A** or R_1' ;

R₁ and **R₁'**, **R₂** and **R₂'** independently of one another are C_1 - C_{18} alkyl or phenyl, or $-(\text{O})_q-\text{SiR}_1\text{R}_1'\text{R}_2$;

R₃ is hydrogen or C_1 - C_6 alkyl,

Y is a divalent group selected from C_1 - C_{10} alkylene, C_2 - C_{10} alkenylene or $-(\text{CH}_2)_b-\text{O}-(\text{CH}_2)_a-$; **a** and **b** are each independently of the other a number of 1 to 6;

IN is a photolabile functional moiety of the formula II or III




R₄ is hydrogen or $-\text{C}(\text{O})-\text{C}(\text{O})-\text{OH}$ or $-\text{C}(\text{O})-\text{C}(\text{O})-\text{OC}_1-\text{C}_6\text{alkyl}$ and **n** is 1-3;

R₅ and **R₆** are C_1 - C_{12} alkyl or together are cyclo C_5 - C_7 alkyl;


R₇ is hydroxy, C_1 - C_6 alkoxy or morpholinyl;

X is $-(\text{CH}_2)_a-$, $-(\text{CH}_2)_b-\text{O}-(\text{CH}_2)_a-$ or $-(\text{CH}_2)_b-\text{O}-\text{CO}-(\text{CH}_2)_a-$;

whereby the process is characterized in that a photolabile functional moiety containing a carboxyl group or an alkylcarboxylate group



is reacted with a carbinol terminated organosilicon compound of the formula IV



wherein **m**, **R₁** and **R₁'**, **R₂** and **R₂'** are as defined above and

B is $-\text{Y}-\text{CHR}_3-\text{OH}$; **B'** is **B** or R_1' ,

in the presence of an enzyme which catalyzes the esterification or transesterification reaction.

Definitions, preferences and availability.Siloxane moiety

The term carbinol terminated organosilicon compound refers to silanes and siloxanes having a $-\text{CH}_2\text{-OH}$ or $-\text{CHR}_3\text{-OH}$ group linked to the Si-unit. The $-\text{CH}_2\text{OH}$ group is preferred.

The term "silanes" refers in this context to oligomers or polymers having a main chain of $-\text{Si-Si-}$ whereas the term "siloxanes" refers to oligomers and polymers having a main chain of $-\text{Si-O-Si-}$.

Preferred are siloxanes having 3-20 Si-units, more preferably 3-10 Si-units.



The residues R_1 and R_1' , R_2 and R_2' are preferably methyl, $-\text{O-Si}(\text{CH}_3)_3$ or $-\text{Si}(\text{CH}_3)_3$.

$\text{C}_1\text{-C}_{18}\text{Alkyl}$ is linear or branched and is for example $\text{C}_1\text{-C}_{12}$ -, $\text{C}_1\text{-C}_8$ -, $\text{C}_1\text{-C}_6$ - or $\text{C}_1\text{-C}_4\text{alkyl}$. Examples are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, iso-butyl, tert-butyl, pentyl, hexyl, heptyl, 2,4,4-trimethyl-pentyl, 2-ethylhexyl, octyl, nonyl, decyl, undecyl, dodecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl or octadecyl.

$\text{C}_1\text{-C}_{12}\text{Alkyl}$, $\text{C}_1\text{-C}_6\text{alkyl}$ and $\text{C}_1\text{-C}_4\text{alkyl}$ have the same definitions as indicated above but with the corresponding number of carbon atoms.

$\text{C}_1\text{-C}_{10}\text{Alkylene Y}$ is linear or branched alkylene, for example $\text{C}_1\text{-C}_8$ -, $\text{C}_1\text{-C}_6$ -, $\text{C}_1\text{-C}_4$ -, $\text{C}_2\text{-C}_8$ -, $\text{C}_2\text{-C}_4\text{alkylene}$, such as methylene, ethylene, propylene, isopropylene, n-butylene, sec-butylene, iso-butylene, tert-butylene, pentylene, hexylene, heptylene, octylene, nonylene or decylene.


In particular, Y is $\text{C}_1\text{-C}_8\text{alkylene}$, for example ethylene, propylene, hexylene, octylene,



- 4 -

C₂-C₁₀Alkenylene is mono- or polyunsaturated, linear or branched and is for example C₂-C₈-, C₃-C₆-, C₂-C₄alkenylene, for example ethenylene, 1-propenylene, 1-butenylene, 3-butenylene, 2-butenylene, 1,3-pentadienylene, 5-hexenylene or 7-octenylene.

The linker group Y may also be a trivalent group such as for example



Trivalent linker groups enable functionalization with two photoinitiator moieties on the same Si-unit.

Some of the carbinol terminated siloxanes of the fomula IV are commercially available, for example from the company Th. Goldschmidt, Essen as Tegomer H--Si 2111; from Witco Corporation as L-7608; from Dow Corning, Midland, Mich., USA under the Q, e.g., QS-5211 product line or from Rhone Poulenc as Rhodorsil 1647 V60.

The carbinol terminated siloxanes may be obtained by methods known to the person skilled in the art, for example by hydrosilylation of an organosilicon compound containing Si-bonded hydrogen (Si-H-group) with an alkene having a hydroxyalkyl functional group such as for example HO-CH₂-CH=CH₂ in the presence of a platinum catalyst. Such methods are described, for example in EP-A-612759 corresponding to US 5,831,080.

The preparation of siloxanes containing hydroxyalkyl groups is also described by K. Tamao et al. Organometallics 1983, 2, 1694.

The preparation of the silanes is described, for example, by B. Kopping et al. J. Org. Chem. 1992, 57, 3994.

Photoinitiator moiety

In one aspect of the invention the photolabile moiety is derived from arylglyoxalates, especially phenylglyoxalates as described in the PCT-Application PCT/EP/01/09123 .

It is of course also possible to use naphthyl- or anthracenyl- glyoxalates or substituted phenylglyoxalates as described in PCT-Application PCT/EP/01/09123.

Substituents are, for example, unsubstituted C₁-C₁₂alkyl or C₁-C₁₂alkyl substituted by OH, C₁-C₄alkoxy, phenyl, naphthyl, halogen, CN and/or -O(CO)C₁-C₈alkyl or -O(CO)phenyl; or are C₂-C₁₂alkyl interrupted by one or more non-successive oxygen atoms; or are C₁-C₁₂alkoxy; C₁-C₁₂alkylthio, C₁-C₁₂alkylamino, diC₁-C₁₂alkylamino; halogen; unsubstituted or C₁-C₄alkyl- and/or C₁-C₄alkoxy-substituted phenyl or are groups -C(O)-C(O)-OH or -C(O)-C(O)-O-C₁-C₈alkyl. If the photolabile moiety "IN" is derived from p-phenylene diglycolic acid, it goes without saying that two carbinol terminated organosilicon compounds may be bound.

However, unsubstituted phenylglyoxalates are preferred.

Some of the phenylglyoxalates are commercially available, for example methyl phenylglyoxylate also known as Genocure MBF, available from Rahn, Inc.

In another aspect of the invention the photolabile moiety is derived from alpha hydroxy-or amino ketones as described in the European Patent Publication EP-A 1072 326 . It is of course also possible to use phenyl substituted alpha hydroxy-or amino ketones wherein possible substituents are the ones listed above.

Enzymes

Enzymes which can be employed in the present invention as catalysts are hydrolases, especially esterases, lipases and proteases as described in U.T. Bornscheuer, R. T. Kazlauskas in: Hydrolases in Organic Synthesis; Wiley-VCH, 1999, Seite 65 -195, ISBN 3-527-30104-6).

Specific examples of esterases are those obtained from animals such as horse liver esterase, pig liver esterase, pig pancreas esterase, fungal esterases or esterases from microorganisms such as from *Bacillus subtilis* or from *Pichia polymorpha*; *Rhizopus* sp.-

esterases, *Penicillium* sp.-esterases or yeast esterases or from *Candida* species, *Alcaligene* species or *Pseudomonas* species.

Lipases suitable for use herein include those of animal, plant and microbiological origin.

Suitable lipases are also found in many strains of bacteria and fungi.

Specific examples are *Polyporus pinsitus* laccase (PPL), (*G. candidum* (GCL), *H. lanuginosa* (HLL), *Rhizopus* sp. (RML, ROL), *Candida* sp. (CAL-A, CAL-B, CCL), *Aspergillus* sp. (ANL), *Pseudomonas* sp. (PCL, PFL).

Examples of suitable proteolytic enzymes are the subtilisins, thermitase, chymotrypsin, thermolysin, papain, aminoacylasen, penicillin amidases or trypsin. Suitable enzymes are known to those skilled in the art and are not limited to the ones mentioned above.

The enzymes can be employed as crude extracts, in pure form or in immobilized form crude or pure, on a support on which they are bound chemically or physically.

Suitable supports are for example silica gel, diatomite, Celite®, Eupergit® (Röhm&Haas, Darmstadt, Deutschland) and the like.

The enzymes can also be employed as cross-linked-enzymes (CLEC's), which enzymes may be obtained from Altus Corp. Suitable enzyme employments are well known and are described, for example, in U.T. Bornscheuer, R. T. Kazlauskas in: *Hydrolases in Organic Synthesis*; Wiley-VCH, 1999, Site 61- 64, ISBN 3-527-30104-6, K. Faber in: *Biotransformation in Organic Chemistry*, Springer 1997, 3rd Ed., 345 - 357, ISBN 3-540-61688-8; H.-J. Rehm, G. Reed In *Biotechnology*, VCH 1998, 2nd, Ed. 407 -411.

Preferred are enzymes that are commercially available (Fluka, Sigma, Novo, Amano, Roche etc) or enzymes that are well known and described , for example, by H.-J. Rehm, G. Reed In *Biotechnology*, VCH 1998, 2nd, Ed. page 40 - 42).

Especially preferred are immobilized lipases, that are thermostable such as Novozyme 435 (recombinante *Candida antarctica* lipase B (E. M. Anderson et al. *Biocat. Biotransf.* 1998, 16, 181), (Firma NOVO Nordisk, Bagsvaerd, Dänemark)) or the Enzyme QLM, QL (Meito Sangyo, Japan).

Enzymes having esterase, lipase and/or protease activity may be obtained from natural sources and/or from microorganism using standard procedures known in the art, for example from cloning processes via expression and amplification.

Process parameters

The enzymatic esterification or transesterification is carried out at low temperatures, especially from 10 - 80°C, preferably from 25- 60°C.

The enzymatic esterification or transesterification can be carried out without adding a solvent or in organic solvents such as for example in hexane, toluene, benzene, THF, diethyl ether, methyl-t.butyl ether, methylene chloride and the like.

The amount of the enzyme catalyst depends on the substrate used and on the reaction conditions such as temperature, reaction time, solvent but may be from 0.01 to 20% by weight, preferably from 1 to 10% by weight based on the modified siloxane employed.

The reaction time depends on the amount used and on the activity of the enzyme catalyst, and is, for example, up to 48 hours, preferably up to 24 hours.

In order to maximize the degree of conversion, it is advantageous to remove the water and/or alkanol of reaction, for example by vacuum distillation.

After the end of reaction, the enzyme catalyst can be separated off by means of appropriate measures, such as filtration or decantation, and can, if desired, be used any number of times.

It is advantageous to use immobilized or unsoluble enzymes. Such methods are described in general by W. Tischer et al. TIBTECH 1999, 17, 326; J. Lalonde, Curr. Oin. Drug Disc. & Develop. 1998, 1(3), 271.

It is also possible to carrying out the process continuously in a appropriate reactor. Such processes are described in general in V. M. Balcao et al. Enzyme Microbiol. Techn. 1996, 18, 392; L. Giorno et al. TIBTECH 2000, 18, 339.

- 8 -

Advantage


Enzymatic processes operate under mild conditions such as low temperatures and under neutral pH conditions. Thus, less byproducts are produced in the inventive process. The enzyme catalyst can be easily separated off as it is not soluble in the organic solvents used. The enzymatic process may also be carried out continuously.

The enzymatic (trans)esterification is not limited to photoinitiators having a, α -ketocarboxylic acid or ester group. It goes without saying that α -ketocarboxylic acids or esters in general may be used for the (trans)esterification reaction.

The following examples are given to illustrate the present invention.


Example 1:

Preparation of



$q=1$, $m=11$, $A=A'=IN-C(O)-O-CH_2-Y-$; IN is Phenyl-CO-, $Y = -(CH_2)_2-$, $R_1=R_1'=R_2=R_2'=CH_3$,

Two equivalents (1.00g) methyl phenylglyoxalate and 1 equivalent (3.20g) of siloxanol of the formula



are dissolved in 3ml toluene at room temperature until a clear solution is obtained. 1.00g of enzyme (Novozym® 435) is added. The reaction tube is placed into a waterbath at 50°C and the reaction mixture is slowly stirred at 50°C under low pressure (250 Torr). When the reaction is complete (results of proton NMR indicated complete reaction) the reaction mixture is diluted with toluene (or another suitable solvent such as, for example ethyl acetate, acetone or methylene chloride). The reaction mixture is filtered to remove the biocatalyst and the solvent is evaporated. If appropriate a filtration over Acrodisc® (CR PTFE, 0.45 μ m) may follow to remove clouding materials.

- 9 -

Yield: 3.60 g (94%) of the above product.

The recovered biocatalyst can be re-used in later reactions.


$^1\text{H-NMR}$ in ppm (CDCl_3 , 200 MHz): 0.00 - 0.06 m (~ 77 H); 0.52 - 0.59 m (4 H); 1.69 - 1.81 m (4 H); 4.28 t ($J = 7.0$ Hz, 4 H); 7.40 - 7.53 m (4 H); 7.55 - 7.61 m (2 H); 7.90 - 7.93 m (4 H).

$^{13}\text{C-NMR}$ in ppm (CDCl_3 , 50 MHz): 0.96; 1.06; 13.87; 22.44; 68.42; 128.56; 129.69; 132.27; 134.50; 163.58; 186.05.

$^{29}\text{Si-NMR}$ in ppm (CDCl_3 , 100 MHz): -21.9; 7.5.


Example 2

Preparation of



$q=1$, $m=7.3$, $A=A'=\text{IN-C(O)-O-CH}_2\text{-Y-}$; IN is Phenyl-CO-, $\text{Y} = \text{-(CH}_2\text{)}_5\text{-}$, $\text{R}_1=\text{R}_1'=\text{R}_2=\text{R}_2'=\text{CH}_3$.

Two equivalents (0.50g) methyl phenylglyoxalate and 1 equivalent (1.22g) of siloxanol of the formula




are dissolved in 5ml toluene at room temperature until a clear solution is obtained. 0.25g of enzyme (Novozym® 435) is added. The reaction is carried out analogue to Example 1 under 150 Torr vacuum

Yield: 33 g (82%) of the above product.

$^1\text{H-NMR}$ in ppm (CDCl_3 , 200 MHz): 0.01 - 0.04 m (~ 48 H); 0.52 - 0.59 m (4 H); 1.26 - 1.43 m (12H); 1.69 - 1.75 m (4 H); 4.34 t ($J = 7.0$ Hz, 4 H); 7.42 - 7.49 m (4 H); 7.57 - 7.63 m (2 H); 7.94-7.96 m (4 H).


$^{29}\text{Si-NMR}$ in ppm (CDCl_3 , 100 MHz): -22.4; -21.9; -21.6; 7.6.

Analogue may be prepared




Example 3

Preparation of



$q=1$, $m=9$, $A=A'=IN-C(O)-O-CH_2-Y-$; IN is Phenyl-CO-, $Y = -CH=CH-$, $R_1=R_1'=R_2=R_2'=CH_3$

5.00g of enzyme (Novozym® 435) is added to a mixture of two equivalents (7.00g) methyl phenylglyoxalate and one equivalent (20.0g) of siloxanol of the formula



The reaction is carried out analogue to Example 1.

Yield: 25.4 g (99 %) of the above product.


1H -NMR in ppm ($CDCl_3$, 200 MHz): 0.00 - 0.04 m (~ 60 H); 3.48 - 3.80 m (8.1 H); 3.90 - 3.92 m (1 H); 3.98 - 4.12 m (4.8 H); 4.47 - 4.54 m (3.3 H); 5.46 - 6.14 m (3.9 H); 7.38 - 7.47 m (4 H); 7.54 - 7.61 m (2 H); 7.92 - 7.95 m (4 H).

^{13}C -NMR in ppm ($CDCl_3$, 50 MHz): diagnostic signals: - 0.44; 0.14; 7.49; 127.72; 133.81; 141.23; 146.70; 162.61; 184.97.

^{28}Si -NMR in ppm ($CDCl_3$, 99.3 MHz): -3.5; -4.1; -20.8; -20.9; -21.9

Example 4


Preparation of



q is 1; $m=1$, $A=IN-C(O)-O-CH_2-Y-$, IN is Phenyl-CO-, $Y = -(CH_3)_3O-(CH_2)-$, $R_1=CH_3$, R_1' , R_2' und $A' = CH_3$, $R_2 = O-Si(CH_3)_3$,

- 11 -

1.50g of enzyme (Novozym® 435) is added to a mixture of two equivalents (2.50g) methyl phenylglyoxalate and one equivalent (5.0g) of siloxanol of the formula



The reaction is carried out analogue to Example 1. When the reaction is complete, the reaction mixture is diluted with methylene chloride.

Yield: 6.30 g (94 %) of the above product.

¹H-NMR in ppm (CDCl₃, 200 MHz): 0.00 s (3 H); 0.07 s (18 H); 0.42 - 0.49 m (2 H); 1.56 - 1.67 m (2 H); 3.44 t (J = 7.0 Hz, 2 H); 3.72 - 3.76 m (2 H); 4.51 - 4.55 m (2 H).

7.44 - 7.51 m (2 H); 7.58 - 7.65 m (1 H); 7.98 - 8.02 m (2 H).

¹³C-NMR in ppm (CDCl₃, 50 MHz): -0.265; 1.93; 13.57; 23.30; 64.97; 67.98; 74.04; 128.72; 129.97; 132.38; 134.71; 163.66; 186.01.

²⁸Si-NMR in ppm (CDCl₃, 99.3 MHz): 7.3, -21.8

The above siloxanol is prepared according to K. Tamao et al. *Organometallics* **1983**, 2. 5.00 g 2-allyloxyethanol (Aldrich) are heated to 80°C under argon. 50 µl of a solution of 0.1 g of hexachloroplatinic acid in 9.9 ml 2-propanol is added. 19.20 ml 1,1,1,3,5,5,5-heptamethyltrisiloxan (Aldrich) are added within 20 minutes. The temperature of the reaction mixture is kept at 80°C until the reaction is completed. 11.80 g (75%) of the above siloxanol is obtained by fractional distillation under high vacuum. (0.08 mbar, 115°C).


¹H-NMR in ppm (CDCl₃, 200 MHz): 0.00 s (3 H); 0.07 s (18 H); 0.41 - 0.47 m (2 H); 1.54 - 1.66 m (2 H); 2.33 breit (OH); 3.41 t (J = 7.0 Hz, 2 H); 3.48 - 3.53 m (2 H); 3.68-3.72 m (2H).

¹³C-NMR in ppm (CDCl₃, 50 MHz): -0.276; 1.92; 13.63; 23.31; 61.80; 71.68; 73.87.

²⁸Si-NMR in ppm (CDCl₃, 99.3 MHz): 7.3, -21.8

Analogues may be obtained.


- 12 -



The photoinitiators as described in the International Application PCT/EP/01/09123 may be prepared analogously.


Example 5

Preparation of



$q=0$; $m=1$, $A = \text{IN}-\text{C}(\text{O})-\text{O}-\text{CH}_2-\text{Y}-$, IN is Phenyl-CO-, $\text{Y} = -(\text{CH}_3)_3\text{Si}-\text{O}-\text{CH}_2-$, $\text{R}_1=\text{R}_2 = -\text{Si}(\text{CH}_3)_3$, R_1' , R_2' und $\text{A}' = \text{CH}_3$,

1.10g of enzyme (Novozym® 435) is added to a mixture of 2 equivalents (1.40g) methyl phenylglyoxalate and 1 equivalent (3.00g) of organosilicon compound of the formula



The reaction tube is placed into a waterbath at 50°C and the reaction mixture is slowly stirred at 50°C under low pressure (250 Torr). When the reaction is complete (results of proton NMR indicated complete reaction) the reaction mixture is diluted with acetone. The reaction

- 13 -

mixture is filtered to remove the biocatalyst and the solvent is evaporated. If appropriate a filtration over Acrodisc® (CR PTFE, 0.45 µm) may follow to remove clouding materials.

Yield: 3.25 g (79%) of the above product.

The recovered biocatalyst can be re-used in later reactions.

¹H-NMR in ppm (CDCl₃, 200 MHz): 0.00 s (27 H); 0.57 – 0.64 m (2 H); 1.46 – 1.57 m (2 H); 3.29 t (2 H, J = 6.7 Hz); 3.58 – 3.62 m (2 H); 4.36 – 4.40 m (2 H); 7.30 – 7.36 m (2 H); 7.44 – 7.51 m (1 H); 7.82 – 7.88 m (2 H).

¹³C-NMR in ppm (CDCl₃, 50 MHz): 1.21; 27.55; 64.93; 67.96; 74.44; 128.93; 129.93; 132.28; 134.81; 163.58; 185.93.

²⁸Si-NMR in ppm (CDCl₃, 99.3 MHz): -12.8, -81.3

The organosilicon product is prepared according to B. Kopping et al. J. Org. Chem. 1992, 57, 3994.

4.00 ml tris(trimethylsilyl)silane (Fluka) and 1.10 g allyloxyethanol (Aldrich) are dissolved in 80 ml under argon atmosphere. 0.44 g azo-isobutyronitril (Fluka) is added. The reaction mixture is heated to 90° C. The temperature of the reaction mixture is kept at 90°C until the reaction is completed. 3.30 g (70%) of the above organosilicon compound is obtained by fractional distillation under high vacuum (0.10 mbar, 100°C).


¹H-NMR in ppm (CDCl₃, 200 MHz): 0.00 s (27 H); 0.56 – 0.62 m (2 H); 1.44 – 1.55 m (2 H); 1.95 breit (OH); 3.25 t (2 H, J = 7.0 Hz); 3.36 t (2 H, J = 4.4 Hz); 3.54 – 3.58 m (2 H).

¹³C-NMR in ppm (CDCl₃, 50 MHz): -0.76; 21.52; 27.02; 59.95; 69.82; 72.58.

²⁸Si-NMR in ppm (CDCl₃, 99.3 MHz): -12.8, -81.3

Example 6


Preparation of



q=1, m=11, A=A'=IN-C(O)-O-CH₂-Y; IN is a group of the formula III with R₅=R₆=methyl, R₇=H, X is -(CH₂)₂-O-CO-(CH₂)₂-, Y = -(CH₂)₂-, R₁=R₂=R₁'=R₂'=CH₃.

- 14 -

Two equivalents (50 mg) of succinic acid ethyl ester 2-[4-(2-hydroxy-2-methyl-propionyl)-phenoxy]-ethyl ester and 1 equivalent (76.6 mg) of siloxanol of the formula



are added to 50 mg of enzyme (Novozym® 435) and the mixture is heated at 45 to 50 °C under a vacuum of 350 mbar for approximately 2 days. The mixture is taken up in toluene, the enzyme removed by filtration and the solvent subsequently removed in vacuo. A filtration over Acrodisc® (CR PTFE, 0.45 µm) may follow to remove clouding materials. Yield: 92 mg (73%) of the above product.


¹H-NMR in ppm (CDCl₃, 300 MHz): -0.01-0.05 (76 H); 0.42-0.55 (4 H); 1.55-1.65 (16 H); 2.56 (8 H); 4.05-4.20 (8 H); 4.41 (4 H); 6.90 (4 H); 8.00 (4 H).

¹³C-NMR in ppm (CDCl₃, 75 MHz): 0.0, 1.1, 13.9, 24.8, 28.6, 28.8, 28.9, 62.4, 62.5, 67.0, 67.1, 69.3, 75.7, 113.9, 114.5, 135.1, 132.1, 161.9, 171.8, 171.9, 202.2.

Succinic acid ethyl ester 2-[4-(2-hydroxy-2-methyl-propionyl)-phenoxy]-ethyl ester is prepared analogous to the preparation described in the European Patent Publication EP-A-1072326 starting from 2-hydroxy-1-(4-hydroxyphenyl)-2-methyl-1-propanone.

Example 7


Preparation of



$q=1$, $m=11$, $A=A'=\text{IN}-\text{C}(\text{O})-\text{O}-\text{CH}_2-\text{Y}$; IN is a group of the formula III with $R_5=R_6=\text{methyl}$, $R_7=\text{H}$, X is $-(\text{CH}_2)_2-\text{O}-(\text{CH}_2)_2-$, Y = $-(\text{CH}_2)_2-$, $R_1=R_2=R_1'=R_2'=\text{CH}_3$,

- 15 -

Two equivalents (50 mg) of 3-{2-[4-(2-Hydroxy-2-methyl-propionyl)-phenoxy]-ethoxy}-propionic acid ethyl ester and 1 equivalent (83 mg) of siloxanol of the formula



are dissolved in 2 ml toluene and 50 mg of enzyme (Novozym® 435) are added. The reaction vessel is cautiously evacuated (20-30 mbar) and after disappearance of the solvent the mixture is heated at 50-60 °C for 1 day. The mixture is taken up in toluene, the enzyme removed by filtration and the solvent subsequently removed in vacuo. A filtration over Acrodisc® (CR PTFE, 0.45 µm) may follow to remove clouding materials.


Yield: 114 mg (87%) of the above product.

¹H-NMR in ppm (CDCl₃, 300 MHz): 0.00-0.04 (~ 77 H); 0.46 (4 H); 1.53-1.65 (16 H); 2.55-2.64 (4 H); 3.97 (4 H); 4.10 (4 H); 4.18 (4 H); 4.40 (4 H); 6.68-6.92 (4 H); 7.97 (4 H).

¹³C-NMR in ppm (CDCl₃, 75 MHz): 0.0, 1.0, 13.9, 22.4, 28.5, 28.8, 28.9, 29.0, 62.4, 65.8, 67.0, 69.3, 75.7, 113.9, 114.5, 127.5, 132.1, 161.9, 171.8, 171.9, 202.2.


Example 8

Preparation of



q=1, m=11, A=A'=IN-C(O)-O-CH₂-Y; IN is a group of the formula III with R₅=R₆=methyl, R₇=H, X is -(CH₂)-, Y = -(CH₂)₂-, R₁=R₂=R₁'=R₂'=CH₃,

Two equivalents (50 mg) of 3-{2-[4-(2-Hydroxy-2-methyl-propionyl)-phenoxy]-ethoxy}-propionic acid ethyl ester and 1 equivalent (76 mg) of siloxanol of the formula



are dissolved in 2 ml toluene and 50 mg of enzyme (Novozym® 435) are added. The reaction vessel is cautiously evacuated (20-30 mbar) and after disappearance of the solvent the

- 16 -

mixture is heated at 50-60 °C for 1 day. The mixture is taken up in toluene, the enzyme removed by filtration and the solvent subsequently removed in vacuo. A filtration over Acrodisc® (CR PTFE, 0.45 µm) may follow to remove clouding materials.


Yield: 102 mg (81%) of the above product.

¹H-NMR in ppm (CDCl₃, 300 MHz): 0.02 (~76 H); 0.45-0.63 (4 H); 1.54-1.66 (16 H); 2.56 (4 H); 3.75-4.2 (8 H); 6.90 (4 H); 7.96 (4 H).

¹³C-NMR in ppm (CDCl₃, 75 MHz): -1.1, 1.0, 13.9, 22.5, 28.6, 34.9, 66.9, 67.2, 69.2, 75.6, 114.0, 114.5, 125.8, 126.9, 132.0, 162.3, 171.1, 202.1

Claims

1. A process for preparing organosilicon group containing photoinitiators of the formula I



m is a number from 1 to 200; **q** is 0 or 1;



A is $\text{IN-C(O)-O-CHR}_3\text{-Y-}$; **A'** is **A** or $R_{1'}$;

R₁ and **R_{1'}**, **R₂** and **R_{2'}** independently of one another are $\text{C}_1\text{-C}_{18}$ alkyl or phenyl, or $-(O)_q\text{-SiR}_1\text{R}_{1'}\text{R}_2$;

R₃ is hydrogen or $\text{C}_1\text{-C}_6$ alkyl,

Y is a divalent group selected from $\text{C}_1\text{-C}_{10}$ alkylene, $\text{C}_2\text{-C}_{10}$ alkenylene or $-(\text{CH}_2)_b\text{-O-(CH}_2)_a\text{-}$; **a** and **b** are each independently of the other a number of 1 to 6;

IN is a photolabile functional moiety of the formula II or III




R₄ is hydrogen or $-\text{C(O)-C(O)-OH}$ or $-\text{C(O)-C(O)-OC}_1\text{-C}_6\text{alkyl}$ and **n** is 1-3;

R₅ and **R₆** are $\text{C}_1\text{-C}_{12}$ alkyl or together are cyclo $\text{C}_5\text{-C}_7$ alkyl;


R₇ is hydroxy, $\text{C}_1\text{-C}_6$ alkoxy or morpholinyl;

X is $-(\text{CH}_2)_a\text{-}$, $-(\text{CH}_2)_b\text{-O-(CH}_2)_a\text{-}$ or $-(\text{CH}_2)_b\text{-O-CO-(CH}_2)_a\text{-}$;

whereby the process is characterized in that a photolabile functional moiety containing a carboxyl group or an alkylcarboxylate group



is reacted with a carbinol terminated organosilicon compound of the formula IV




wherein **m**, **R₁** and **R_{1'}**, **R₂** and **R_{2'}** are as defined above and

B is $-\text{Y-CHR}_3\text{-OH}$; **B'** is **B** or $R_{1'}$,


in the presence of an enzyme which catalyzes the esterification or transesterification reaction.

2. A process for preparing siloxane group containing photoinitiators of the formula I according to claim 1, wherein q is 1 and IN is a photolabile functional moiety of the formula II




and whereby the enzyme is selected from esterases, lipases or proteases.

3. A process for preparing siloxane group containing photoinitiators of the formula I according to claim 1, wherein q is 1 and IN is a photolabile functional moiety of the formula III



and whereby the enzyme is selected from esterases, lipases or proteases.

4. A process for preparing organosilicon group containing photoinitiators of the formula I according to claim 1, wherein q is 0 and IN is a photolabile functional moiety of the formula II




and whereby the enzyme is selected from esterases, lipases or proteases.

5. A process to any one of claims 1 to 4, wherein the enzyme is immobilized on a support.

6. A process to any one of claims 1 to 5, wherein the reaction is carried out at a temperature in the range from 25°C to 60°C.

Abstract:

The invention relates to a process for preparing organosilicon group containing photoinitiators of the formula I





m is a number from 1 to 200; **q** is 0 or 1;

A is $\text{IN}-\text{C}(\text{O})-\text{O}-\text{CHR}_3-\text{Y}-$; **A'** is **A** or $\text{R}_{1'}$; R_3 is hydrogen or C_1-C_6 alkyl, R_1 and $\text{R}_{1'}$, R_2 and $\text{R}_{2'}$ independently of one another are C_1-C_{18} alkyl or phenyl, or $-(\text{O})_q-\text{SiR}_1\text{R}_{1'}\text{R}_2$;

Y is a divalent group selected from C_1-C_{10} alkylene, C_2-C_{10} alkenylene or $-(\text{CH}_2)_b-\text{O}-(\text{CH}_2)_a-$; **a** and **b** are each independently of the other a number of 1 to 6;

IN is a photolabile functional moiety of the formula II or III



R_4 is hydrogen or $-\text{C}(\text{O})-\text{C}(\text{O})-\text{OH}$ or $-\text{C}(\text{O})-\text{C}(\text{O})-\text{OC}_1-\text{C}_6$ alkyl and **n** is 1-3;

R_5 and R_6 are C_1-C_{12} alkyl or together are cyclo C_5-C_7 alkyl;


R_7 is hydroxy, C_1-C_6 alkoxy or morpholinyl;

X is $-(\text{CH}_2)_a-$, $-(\text{CH}_2)_b-\text{O}-(\text{CH}_2)_a-$ or $-(\text{CH}_2)_b-\text{O}-\text{CO}-(\text{CH}_2)_a-$;

whereby the process is characterized in that a photolabile functional moiety containing a carboxyl group or an alkylcarboxylate group



is reacted with a carbinol terminated organosilicon compound of the formula IV



wherein **m**, R_1 and $\text{R}_{1'}$, R_2 and $\text{R}_{2'}$ are as defined above and

B is $-\text{Y}-\text{CHR}_3-\text{OH}$; **B'** is **B** or $\text{R}_{1'}$,

in the presence of an enzyme which catalyzes the esterification or transesterification reaction.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.